E645 **EPDM**



Value

Standard





EPDM 70 SHEETING Drinking Water - WRAS certification

MECHANICAL, PHYSICAL AND CHEMICAL PROPERTIES

MECHANICAL

Measured characteristics

FEAT	URES
Plack	

Black EPDM sheeting for drinking water. Approved by WRAS as suitable for contact with water for domestic purposes up to 23°C.

REGULATIONS

WRAS approval num 1406533: This product has satisfied the criteria set out in BS 6920: Part 1: 2000 "Specification" and thus complies with the requirements of the Water Regulations Advisory Scheme Tests of Effect on Water Quality (BS 6920: 2000).

APPLICATIONS

Gaskets or washers cutting and manufacturing of pieces for general industrial purpose applications in contact with drinking water.

ADVANTAGES

- Very good resistance to ozone and ageing
- Excellent temperature resistance (-40/+120 °C) 1
- Good ratio quality/price 1
- Matte finish to guarantee a good surface finished quality to secure an easy unrolling.

BENEFITS

- 1 Performance
- Legality
- Hygiene, cleanliness 1
- Food safety Т

MAINTENANCE RECOMMENDATION

Always follow manufacturer warnings and instructions when using any cleaning product.

MECHANICAL						
		EPDM	I			
		1.15 ±0.05	g/cm ³			
	ASTM D2240	70 ±5	Shore A			
	ISO 37	≥12	MPa			
	ISO 37	≥400	%			
	ISO 34-1	≥35	N/mm			
Comp	ISO 815-1	≤25	%			
TEMPERATURE						
		-40/+120	°C			
AGEING						
	ASTM D573	≤5	Shore A			
ΔTens	ASTM D573	≤-10	%			
∆ Elongati	ASTM D573	≤-30	%			
Ozone resistance	ASTM D1149 Typ A	No crack				
	ISO 1817	0				
CHEMICAL RESISTANCE						
Diluted acids and bases	Concentrated acids and bases	Ozone	Oils and hydrocarbons			
Very good	Good	Very good	Non su	litable		
IDENTIFICATION						
Branding	Without.					
Packaging	Thickness ≤6mm rolled on cardboard tube Ø 80mm. Thickness >6mm in roll.					
Wrapping	Black polyethylene film.					
Labelling	Self-adhesive label indicating product name, dimensions, area in m2, nominal					

Unless typographical error, information and figures of our technical datasheet are based on our experience and laboratory tests according to international standards. This data is intended to be used as a guideline only. Material performance depends on the conditions of use and the final application.

weight, and product code to allow product traceability.

EPDM	EPDM 70 SHEETING	E645		
THICKNESS	WIDTH	LENGTH m	WEIGHT kg/m ²	SIDES FINISH
1.5±0.25	1400 ± 2 %	15±2%	1.72	1 SMOOTH SIDE/1 SHINY SIDE
2±0.3	1400 ± 2 %	15±2%	2.29	1 SMOOTH SIDE/1 SHINY SIDE
3±0.3	1400 ± 2 %	10 ± 2 %	3.44	1 SMOOTH SIDE/1 SHINY SIDE
4±0.4	1400 ± 2 %	10 ± 2 %	4.59	1 SMOOTH SIDE/1 SHINY SIDE
5±0.4	1400 ± 2 %	10 ± 2 %	5.73	1 SMOOTH SIDE/1 SHINY SIDE

